

# R1-2145

# Extremely tough, high durometer, fast-cure adhesive/sealant

#### **DESCRIPTION**

- Two-part, gray silicone adhesive system
- Cures at room temperature or rapidly by applying heat in an oven or by a heat gun or lamp
- Does not require atmospheric moisture to cure
- No curing byproducts such as acetic acid or methyl alcohol
- Product available in easy-to-use, airless side-by-side kits that eliminate mixing and deairing difficulties
- 1:1 Mix Ratio (Part A: Part B)

#### **APPLICATION**

- Adhesive for bonding and sealing silicones to each other and other substrates such as metals and plastics
- For rapid production or prototyping due to a rapid cure

### **PROPERTIES**

| Typical Properties             | Average Result      | Standard        | NT-TM |
|--------------------------------|---------------------|-----------------|-------|
| Uncured:                       |                     |                 |       |
| Appearance, Part A             | Black               | ASTM D2090      | 002   |
| Appearance, Part B             | White               | ASTM D2090      | 002   |
| Color, Mixed                   | Dark Gray           | -               | -     |
| Extrusion Rate, Part A         | 280 g/min           | ASTM C603       | 033   |
| Extrusion Rate, Part B         | 290 g/min           | ASTM C603       | 033   |
| Work Time                      | 1 hour              | -               | 008   |
| Cured: 2 hours at 65°C (149°F) |                     |                 |       |
| Specific Gravity               | 1.16                | ASTM D792       | 003   |
| Durometer, Type A              | 45                  | ASTM D2240      | 006   |
| Tensile Strength               | 1,000 psi (6.9 MPa) | ASTM D412, D882 | 007   |
| Elongation                     | 400%                | ASTM D412, D882 | 007   |
| Tear Strength                  | 190 ppi (33.5 N/mm) | ASTM D624       | 009   |
| Stress at 200% Strain          | 525 psi (3.6 MPa)   | ASTM D412, D882 | 007   |



| Typical Properties           | Average Result             | Standard   | NT-TM |
|------------------------------|----------------------------|------------|-------|
| Lap Shear, unprimed          | 145 psi (1.0 MPa)          | ASTM D1002 | 010   |
| Lap Shear, primed w/ CF1-135 | 625 psi (4.3 MPa)          | ASTM D1002 | 010   |
| 180° Peel, primed w/ CF1-135 | 50 ppi (8.8 N/mm)          | ASTM D903  | 104   |
| Young's Modulus              | 300 psi (2.1 MPa)          | -          | -     |
| Dielectric Strength          | 825 Volts/mil (32.5 kV/mm) | ASTM D149  | -     |

#### **INSTRUCTIONS FOR USE**

#### **Mixing**

Mix at a 1:1 mix ratio when extracted from their side-by-side kits through a static mix and dispense cartridge. Attach the disposable static mix tip to the cartridge and extrude the product directly onto the substrate.

Note: NuSil Technology recommends discarding the first few arams of extruded material.

Can also be purchased in standard two-part kits. When using standard kits, take care to minimize air entrapped while mixing. Place the mixed product in a vacuum chamber to remove entrapped air and subsequently reduce bubble formation during curing.

#### **Substrate Consideration**

Cures in contact with most materials common to electrical and electronic assemblies. Exceptions include: sulfur cured organic rubbers, latex, chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents. Clean units being encapsulated or potted to ensure they are free of contaminants. Also clean and dry containers and dispensers being used. Prevent cure inhibition by washing all containers with clean solvent or volatizing the contaminants by heating.

Note: Some bonding applications may require use of a primer. NuSil Technology CF1-135 silicone primer is recommended.

#### Adjustable Cure Schedule

Product cures at a wide range of cure times and temperatures to accommodate different production needs. Contact NuSil Technology for details.

## **Packaging**

50 ml SxS Kit 400 ml SxS Kit 2 Pint Kit (910 g) 2 Gallon Kit (7.28 kg) 10 Gallon Kit (36.4 kg)

# Warranty

12 Monhts

#### **SPECIFICATIONS**

Do not use the properties shown in this technical profile as a basis for preparing specifications. Please <u>contact</u> NuSil Technology for assistance and recommendations in establishing particular specifications.

#### WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC (hereinafter "NuSil Technology") is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil Technology provides a specific written warranty of fitness for a particular use, NuSil Technology's sole warranty is that the product will meet NuSil Technology's then current specification. NuSil Technology specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil Technology's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be other than as



warranted. NuSil Technology expressly disclaims any liability for incidental or consequential damages.

#### WARNINGS ABOUT PRODUCT SAFETY

NuSil Technology believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil Technology cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil Technology makes no warranty concerning fitness for any use or purpose. NuSil Technology has completed no testing to establish safety of use in any medical application.

NuSil Technology has tested this material only to determine if the product meets the applicable specifications. (Please <u>contact</u> NuSil Technology for assistance and recommendations when establishing specifications.) When considering the use of NuSil Technology products in a particular application, review the

latest Material Safety Data Sheet and <u>contact</u> NuSil Technology with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

#### PATENT / INTELLECTUAL PROPERTY WARNING

NuSil Technology disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil Technology does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process.