

# CF19-2615

## Optically clear potting and encapsulating silicone elastomer

### DESCRIPTION

- Two-part, optically clear, solvent free, low viscosity silicone
- Cures at room temperature or rapidly with heat
- Offers good physical and electrical stability across a broad range of temperatures
- Convenient 1:1 Mix ratio

### APPLICATION

- To provide protection of electronic components and assemblies against shock, vibration, moisture, ozone, dust, chemicals and other environmental hazards by potting or encapsulating
- For photonics applications such as HBLEDs, photo detectors, lasers, discrete optics and flat panel displays that require a 1.41 refractive index

### PROPERTIES

Typical Properties	Average Result	Metric Conv.	Standard	NT-TM
<b>Uncured:</b>				
Appearance	Optically Clear	-	ASTM D2090	002
Viscosity, Part A	1,300 cP	1,300 mPas	ASTM D1084, D2196	001
Viscosity, Part B	800 cP	800 Mpas	ASTM D1084, D2196	001
Work Time	4 hours	-	-	008
<b>Cured: 30 minutes at 150°C (302°F)</b>				
Operating Temperature Range	-85 to 465°F	-65 to 240°C	-	-
Durometer, Type A	30	-	ASTM D2240	006
Tensile Strength	120 psi	0.9 MPa	ASTM D412, D882	007
Elongation	100 %	-	ASTM D412, D882	007
Refractive Index	1.41	-	ASTM D1747, D1218	018
Dielectric Strength	500 volts/mil	19.7 kV/mm	ASTM D149	-
Volume Resistivity	1 x 10 <sup>15</sup>	-	ASTM D257	040

The test data shown for this material is the average value for typical properties. All of these properties may not be tested on a lot to lot basis and cannot be used to draft specifications. Please [contact](#) NuSil® for assistance and recommendations in establishing limits for product specifications

## INSTRUCTIONS FOR USE

### Mixing

Mix in a 1:1 ratio Part A to Part B, taking care to minimize air entrapment during mixing.

### Substrate Considerations

Cures in contact with most materials common to electronic assemblies. Exceptions include butyl and chlorinated rubbers, some RTV silicones and unreacted residues of some curing agents. Units being encapsulated or potted should be clean and free of surface contaminants. Containers and dispensers being used should also be clean and dry. Cure inhibition can usually be prevented by washing all containers with cleaning solvent or volatilizing the contaminants by heating.

Note: Some bonding applications may require the use of a primer. NuSil CF1-135 silicone primer is recommended.

### Vacuum Deaeration

Remove air entrapped during mixing by common vacuum deaeration procedure, observing all applicable safety precautions. Slowly apply vacuum, up to 28 inches Hg, to a container rated for use and of volume at least four times that of material being deaerated. Hold vacuum until presence of air is no longer evident.

### Adjustable Cure Schedule

Product cures at room temperature and a wide range of elevated temperatures and cure times to accommodate different production needs. Contact NuSil for details.

## SPECIFICATIONS

Do not use the typical properties shown in this technical profile as a basis for preparing specifications. Please [contact](#) NuSil for assistance and recommendations in establishing limits for product specifications.

## WARRANTY INFORMATION

The warranty period provided by NuSil Technology LLC is 12 months from the date of shipment when stored below 40°C in original unopened containers. Unless NuSil provides a specific written warranty of fitness for a particular use, NuSil's sole warranty is that the product will meet NuSil's then current specification. NuSil specifically disclaims all other expressed or implied warranties, including, but not limited to, warranties of merchantability and fitness for use. The exclusive remedy and NuSil's sole liability for breach of warranty is limited to refund of purchase price or replacement of any product shown to be

### Packaging

400 ml SxS Kit (0.42 kg)  
2 Pint Kit (0.910 kg)  
2 Gallon Kit (7.28 kg)  
10 Gallon Kit (36.4 kg)

### Warranty

12 Months

other than as warranted. NuSil expressly disclaims any liability for incidental or consequential damages.

## WARNINGS ABOUT PRODUCT SAFETY

NuSil believes, to the best of its knowledge, that the information and data contained herein are accurate and reliable. The user is responsible to determine the material's suitability and safety of use. NuSil cannot know each application's specific requirements and hereby notifies the user that it has not tested or determined this material's suitability or safety for use in any application. The user is responsible to adequately test and determine the safety and suitability for their application and NuSil makes no warranty concerning fitness for any use or purpose. NuSil has completed no testing to establish safety of use in any medical application.

NuSil has tested this material only to determine if the product meets the applicable specifications. (Please [contact](#) NuSil for assistance and recommendations when establishing specifications.) When considering the use of NuSil products in a particular application, review the latest Material Safety Data Sheet and [contact](#) NuSil with any questions about product safety information.

Do not use any chemical in a food, drug, cosmetic, or medical application or process until having determined the safety and legality of the use. The user is responsible to meet the requirements of the U.S. Food and Drug Administration (FDA) and any other regulatory agencies. Before handling any other materials mentioned in the text, the user is advised to obtain available product safety information and take the necessary steps to ensure safety of use.

## PATENT / INTELLECTUAL PROPERTY WARNING

NuSil disclaims any expressed or implied warranty against the infringement of any domestic or international patent/intellectual property right. NuSil does not warrant the use or sale of the products described herein will not infringe the claims of any domestic or international patent/intellectual property right covering the product itself, its use in combination with other products, or its use in the operation of any process